

National Distribution 888-380-5575

HYBRID PEDESTAL SYSTEM


FIRE TESTING - ASTM-D1929

	RATORIES	8385 White Oak Avenue Rancho Cucamonga, CA 91730 909.483.0250 ph. 909.483.0336 fr
CLIENT: TILE TECH 4730 East 26 Vernon, CA	S th Street	
Test Re	oort No: RJ3897-1	Date: March 27, 2015
SAMPLE ID:	The following test material wa page 2.	as identified as Tile Tech Hybrid Pedestal. See photos o
SAMPLING DETAIL:	Test samples were submitted to the laboratory directly by the client. No special sampling conditions or sample preparation were observed by QAI.	
DATE OF RECEIPT:	Samples were received on March 24, 2015.	
TESTING PERIOD:	March 26 & 27, 2015.	
AUTHORIZATION:	Testing authorized by Ronnie Tabibnia.	
TEST REQUESTED:	ASTM D1929-13a. "Standard Test Method for Determining Ignition Temperatures of Plastic". Self Ignition temperature.	
TEST RESULTS:	Self-Ignition Temperature	Number of Specimens Tested
	800° F (427° C)	5
OBSERVATIONS:	Flaming combustion was observed. Moderate smoke evolution was noted.	
REQUIREMENTS:	International Building Code, 2012 Edition, Section 2606.4 Specifications. Light- transmitting plastics, including thermoplastic, thermosetting or reinforced thermosetting plastic material, shall have a self-ignition temperature of 650°F (343°C) or greater where tested in accordance with ASTM D 1929.	
CONCLUSION:	The submitted sample meets	the requirements.
Prepared By		Signed for and on behalf of QAI Laboratories, Inc.
Brin Onteg	a.	273-69
Brian Ortega Test Technician		Greg Banasky Senior Technician
	PROPERTY OF THE CLIENT ADDRESSED. THE REP APPROVAL FROM QAI. ANY LIABILITY ATTACHED T	age 1 of 1 DRT MAY ONLY BE REPRODUCED IN FULL. PUBLICATION OF EXTRACTS FROM THIS REPORT I HERETO IS LIMITED TO THE FEE CHARGED FOR THE INDIVIDUAL PROJECT FILE REFERENCED ONLY TO THE SPECIFIC SAMPLE(S) EVALUATED.
		Qqai.org



National Distribution 888-380-5575

HYBRID PEDESTAL SYSTEM FIRE TESTING - ASTM-D1929





National Distribution 888-380-5575

HYBRID PEDESTAL SYSTEM FIRE TESTING - ASTM-D1929

